

This is the peer reviewed version of the following article:

“ImPACT” FIRB Futuro in Ricerca: Structural characterization of fluorenone-zeolite L host-guest complex / Gigli, Lara; Arletti, R.; Fois, E.; Martra, G.; Tabacchi, G.; Vitillo, J. G.; Vezzalini, Maria Giovanna; Quartieri, S.. - STAMPA. - 1:(2013), pp. 53-53. (Intervento presentato al convegno XVII National Congress of Catalysis GIC 2013 and XI National Congress of zeolites Science and Technology tenutosi a Riccione nel September, 15-18, 2013).

-
Terms of use:

The terms and conditions for the reuse of this version of the manuscript are specified in the publishing policy. For all terms of use and more information see the publisher's website.

16/07/2024 06:06

(Article begins on next page)

**"ImPACT"- FIRB Futuro in Ricerca:
Pressure-induced supermolecular organization
of water and ethanol in all-silica zeolites**

R. Arletti¹, G. Vezzalini², S. Quartieri³

¹ Earth Sciences Department, UNITO, Torino, Italy.

² Department of Chemical and Geological Sciences, UNIMORE, Modena, Italy.

³ Department of Physics and Earth Sciences, UNIME, Messina, Italy

Corresponding author's email address: rossella.arletti@unito.it

One of the purposes of "ImPact" Project (financed by Italian MIUR, FIRB- Futuro in Ricerca 2013-2016) is to understand at atomistic level the supramolecular organization of different molecules in zeolites frameworks. In particular, the pressure-induced aggregation of molecules in high-silica zeolites cavities of different shapes (FER, MOR, MFI, CHA) will be studied. Water in zeolites represents a model system for a wide range of experimental as well as theoretical investigations, aimed at understanding the effect of confinement on the structure, dynamics and thermodynamics of molecular fluids [1-3]. Understanding the behaviour of nano-confined water is also relevant to such important problems as transport in ion channels, moreover, from a practical point of view, water plays a key role in many applications of zeolites such as ion-exchange and liquid phase separation [4-5].

In this paper the HP-induced confinement of water and ethanol in all-silica ferrierite [s.g Pnmm, $a=14.0690(8)$ Å, $b=7.4177(3)$ Å, $c=18.708(1)$ Å $V=1952.3(2)$ Å³] compressed with two different aqueous media [(methanol-ethanol-water (16:3:1; m.e.w.); ethanol-water (1:3; e.w.)), is presented and the structural features of the HP phase is discussed. The HP SR-XRPD experiments were performed at the BM01 beam line (European Synchrotron Radiation Facilities, Grenoble, France). While for m.e.w. experiment it was possible to collect data up to 8 GPa, the e.w. ramp was stopped at 1.3 GPa due to ice formation. In the range Pamb-8 GPa, the contraction of a, b, c and V observed in m.e.w. are: 5.8, 5.0, 7.2 and 16.9%, respectively. From Pamb to 1.3 GPa, a unit cell volume reduction of about 3.4 % is observed for ferrierite compressed in e.w, and the corresponding contraction of a, b, c and V cell parameters are 1.3, 0.9, 1.1 and 3.4%, %, respectively. Structural refinements were performed by Rietveld profile fitting in the whole pressure range in e.w. and up to 0.2 GPa in m.e.w. (the data quality of the higher pressure patterns being too low for structural refinement). In both cases no phase transitions are observed and the unit cell parameters of Pamb are recovered upon decompression. The structural results indicated the penetration of the pressure media even at the lowest investigated pressure in both experiments.

In ferrierite compressed in e.w., a chain of water (w) and ethanol molecules (e) running along the central axis of the channels was localized even at 0.2 GPa, accounting for a total of 5 w and 3.6 e molecules. The increase of the occupancy factors of the localized sites led a total load of 11 w and 4 e molecules at 1 GPa. The refinement at 0.2 GPa of ferrierite compressed in m.e.w. indicated the penetration of only water (15.6 molecules) organized in chains. The interactions among these molecules and the framework oxygen atoms are very weak, due to the hydrophobicity of the framework.

- References.** [1] Ohba T., Kanoh H., Kaneko K., J. (2004): *Am. Chem. Soc.*, **126**, 1560–1562. [2] Devautour S., Abdoulaye S. A., Giuntini J.-C., Henn F. (2001): *J. Phys. Chem. B*, **105**, 9297–9301. [3] Demontis P., Suffritti G. B. (1997): *Chem. Rev.*, **97**, 2845–2878. [4] Beckstein O., Sansom M. S. P. (2003): *Proc. Natl. Acad. Sci. U. S. A.*, **100**, 7063–7068. [5] Hummer G., Rasaiah J.-C., Noworyta J. P. (2001): *Nature*, **414**, 188–190.