This is the peer reviewd version of the followng article:

Structural properties of adsorbent phyllosilicates rule the entrapping ability of intercalated ironphenanthroline complex towards thiols / Castellini, E.; Malferrari, D.; Bernini, F.; Mucci, A.; Borsari, M.; Brigatti, M. F., - In: MICROPOROUS AND MESOPOROUS MATERIALS. - ISSN 1387-1811. - 285:(2019), pp. 150-160. [10.1016/j.micromeso.2019.04.054]

Terms of use:

The terms and conditions for the reuse of this version of the manuscript are specified in the publishing policy. For all terms of use and more information see the publisher's website.

28/04/2024 04:28



Contents lists available at ScienceDirect

Microporous and Mesoporous Materials



journal homepage: www.elsevier.com

Structural properties of adsorbent phyllosilicates rule the entrapping ability of intercalated iron-phenanthroline complex towards thiols

Elena Castellini, Daniele Malferrari*, Fabrizio Bernini, Adele Mucci, Marco Borsari, Maria Franca Brigatti

Department of Chemical and Geological Sciences, University of Modena and Reggio Emilia, Via Campi 103, I-41125 Modena, Italy

ARTICLE INFO

Keywords: clays Sepiolite Iron Phenanthroline Hybrid materials Gas trapping Sulfur

$A\,B\,S\,T\,R\,A\,C\,T$

The interaction of volatile organic sulfur derivatives, such as 1-heptanethiol ($C_2H_{16}S$), with clay minerals treated with a μ -oxo Fe³⁺-phenanthroline 1:1 complex results strongly affected by crystal chemical properties of pristine mineral phases. In particular, two sepiolite clays with different structural features demonstrated significantly different ability to immobilize the Fe³⁺-phenanthroline complex at two pH values (pH = 5.4 and pH = 2.3). The most effective binding was obtained with sepiolite with higher structural disorder at pH 5.4. Accordingly, the resulting hybrid material showed also the greatest efficiency in removal of thiol in gas phase. A direct correlation can be established between the adsorption of the Fe³⁺-phenanthroline complex and the gas binding process at room temperature. In fact, 1-heptanethiol entrapping occurs via redox reactions between Fe³⁺ and a first thiol molecule to give the reduced Fe²⁺-phenanthroline complex and disulfide, followed by the binding of further thiols to the reduced metal centre. The extremely high amount of thiol immobilized by the hybrid material also suggests the co-presence of a catalytic mechanism that guarantees the reoxidation of Fe⁺² to Fe⁺³ and the restoration of redox reactions with thiol. Investigation and conclusions were supported by the several experimental techniques: elemental analysis, X-ray powder diffraction analyses, UV–Vis measurements, FT-IR and NMR spectroscopies, thermogravimetric analyses.

1. INTRODUCTION

Volatile organic sulfur derivatives, such as 1-heptanethiol ($C_7H_{16}S$), are smelly pollutants commonly observed in natural environments and as a result of human activities. The immobilization of sulfur-bearing gas phases is thus a key target in environmental remediation.

Sepiolite, with ideal half-cell composition Mg₈Si₁₂O₃₀(OH)₄·4(OH₂)·nH₂O, is a fibrous octahedral Mg-rich layer silicate typically occurring as fine-grained, poorly crystalline aggregate [1,2]. The widely accepted structure model, in the orthorhombic space group Pnan, was firstly proposed in 1956 by Brauner and Preisinger Sepiolite structure (unit cell parameters [3]. $a \times b \times c = 13.405 \times 27.016 \times 5.275 \text{ Å}^3$, $\alpha = \beta = \gamma = 90^{\circ}$) consists

of an alternation of blocks and cavities that grow up along the fibres direction (*c*-axis). Each block consists of two tetrahedral sheets (T) sandwiching an octahedral sheet (M). The T sheet is continuous, thanks to a periodic inversion in the orientation of the apical oxygen atoms, which point alternatively up and down, bonding either to the upper or to the lower discontinuous M sheet. Each block is connected to its neighbour through an inverted Si—O—Si bond. Tunnels measure approximately $3.7 \times 10.6 \text{ Å}^2$ in cross section and account in large part for the high specific surface area and excellent sorption properties related to several active sites, i.e., i) OH-anions coordinated to Mg octahedral sites; ii) structural H₂O which completes the Mg octahedral site coordination at the edge of the tunnels; iii) four zeolitic H₂O positions inside sepiolite tunnels [4,5] (Fig. 1). Furthermore, the periodic inver-

https://doi.org/10.1016/j.micromeso.2019.04.054

Received 11 October 2018; Received in revised form 29 March 2019; Accepted 23 April 2019 Available online xxx 1387-1811/ © 2019.

Abbreviations: SP1, Sepiolite SP-1 (Valdemoro, Spain); EB, Sepiolite EB (Elbuur, Central Somalia); $Fe^{3+}phen$, $[(OH_2)_3(Phen)FeOFe(Phen)(OH_2)_3]^{-4}$; HPT, 1-heptanethiol; SP1-Fe³⁺phen_{pH=2.3}, solid hybrid material made by sepiolite SP1 treated with Fe³⁺phen complex at pH = 2.3; SP1-Fe³⁺phen_{pH=5.4}, solid hybrid material made by sepiolite SP1 treated with Fe³⁺phen complex at pH = 2.3; EB-Fe³⁺phen_{pH=5.4}, solid hybrid material made by sepiolite SP1 treated with Fe³⁺phen complex at pH = 2.3; EB-Fe³⁺phen_{pH=5.4}, solid hybrid material made by sepiolite EB treated with Fe³⁺phen complex at pH = 2.3; EB-Fe³⁺phen_{pH=5.4}, solid hybrid material made by sepiolite SP1 treated with Fe³⁺phen complex at pH = 2.3 and one-week exposed to 1-heptanethiol; SP1-Fe³⁺phen_{pH=5.4}+PPT, solid hybrid material made by sepiolite EB treated with Fe³⁺phen complex at pH = 5.4 and one-week exposed to 1-heptanethiol; EB-Fe³⁺phen_{pH=5.4}+PPT, solid hybrid material made by sepiolite EB treated with Fe³⁺phen complex at pH = 5.4 and one-week exposed to 1-heptanethiol; EB-Fe³⁺phen_{pH=5.4}+PPT, solid hybrid material made by sepiolite EB treated with Fe³⁺phen complex at pH = 2.3 and one-week exposed to 1-heptanethiol; EB-Fe³⁺phen_{pH=5.4}+PPT, solid hybrid material made by sepiolite EB treated with Fe³⁺phen complex at pH = 5.4 and one-week exposed to 1-heptanethiol; EB-Fe³⁺phen_{pH=5.4}+PPT, solid hybrid material made by sepiolite EB treated with Fe³⁺phen complex at pH = 2.3 and one-week exposed to 1-heptanethiol; EB-Fe³⁺phen_{pH=5.4}+PPT, solid hybrid material made by sepiolite EB treated with Fe³⁺phen complex at pH = 5.4 and one-week exposed to 1-heptanethiol.

^{*} Corresponding author.

Email address: daniele.malferrari@unimore.it (D. Malferrari)



Fig. 1. Sepiolite crystal-structure, viewed along *c* axis. The drawing was obtained using atomic coordinates reported by Post et al. (2007) [4]. The repetition of discontinuous octahedral (M) and continuous tetrahedral sheets (T) creates tunnels, *c*-axis elongated, filled by weakly-bound zeolitic H₂O (circles). Unit cell is outlined by continuous lines.

sion of the tetrahedra introduces additional active sites on the "external surface" of the mineral fibres [4]. OH groups on the external surface originate as a result of broken Si-O-Si bonds, balancing their residual charge by accepting a proton to form Si-OH groups which can react with several molecules by formation of different bonding.

Due to its unique structure and specific physico-chemical properties, sepiolite is used as an adsorbent, decolorizing agent, catalyst or catalyst carrier [1,6,7] and as an inorganic membrane for ultra-filtration [8]. Furthermore sepiolite, together with palygorskite (a modulated layer silicate where tunnels measure of 3.7×6.0 Å²in cross section) and indigo (C₁₆H₁₀N₂O₂), forms the famous Maya Blue pigment, well known in Cultural Heritage for its outstanding stability [9–11].

Owing to its strong interfacial properties, sepiolite was proposed as an adsorbent of organic and metallo-organic molecules [6,11,13–16]. Small polar molecules, such as ammonia, methanol, acetone, and ethylene glycol can be easily incorporated into the sepiolite tunnels [6,12], as well as much larger compounds like hexane, benzene, pyridine, methylene blue, indigo, and cetyltrimethylammonium bromide [14–16]. However, reactions with polar molecules can be affected by chemical substitutions in mineral structure as well as by different mineral morphology [17]. Computational studies were carried out to explain the diffusion process of organic compounds inside the sepiolite tunnels. More specifically, a molecular dynamics study [10,11] and an approach based on density functional theory computation [18] indicated that indigo can be easily accommodated into the sepiolite tunnels as well as pyridine, methylene blue, and quaternary amines [19].

Some previous studies dealing with the intercalation of lamellar layered silicates, such as montmorillonite, with cationic metal complexes, specifically Fe^{3+} phenanthroline, showed that modifications by ion exchange reactions provide larger spacing between layers [20,21]. In these layer silicates, Fe^{3+} -phenanthroline complex, both on external surfaces and in the interlayer, assumes a bi-dimensional disposition. Montmorillonite treated with Fe^{3+} phenanthroline can be used for the removal of sulfur containing phases from waste gasses [22,23], similarly to synthetic phases commonly used for the same purpose [24]. In sepiolite, hosted molecules, such as indigo, are expected to interact with water located inside structural channels due to the absence of layer charge and the needle-like morphology of the mineral, thus defining a linear rather than a bi-dimensional distribution [10,25].

In this study, a new hybrid material, i.e., sepiolite functionalized with the μ -oxo 1:1 Fe—phenanthroline complex [(OH₂)₃(phen)Fe-

OFe(phen)(OH₂)₃] (SO₄)₂ (hereafter Fe³⁺phen) [26] was prepared as a novel and efficient adsorbent material to remove sulfur-bearing gases, such as 1-heptanethiol. Two sepiolite samples were considered, i.e., sepiolite from Valdemoro (Spain) and from Elbuur (Somalia) characterized by a long and by an intermediate fiber morphology, respectively. The aims of our study are 1) to prepare and characterize the sepiolite-Fe³⁺phen hybrid material; 2) to investigate the effects and the mechanisms that enhance the Fe³⁺phen adsorption on sepiolite; 3) to test the immobilization at room temperature of sulfur-bearing gases (1-heptanethiol was used as reference) by the new hybrid material; 4) to explain if the crystal chemical and morphological features of sepiolite affect the Fe³⁺phen adsorption and 1-heptanethiol capture.

2. EXPERIMENTAL

2.1. Materials

Materials used in this work consists of:

- i) Sepiolite from Elbuur mine in the Galmudug Regional State, central Somalia, 360 km North West from Mogadishu (hereafter referred as EB). Mineralogical and chemical features of this sample, were discussed in previous works [27–30]. Sepiolite, associated to minor content of calcite and traces of quartz and halite, were sampled at depths ranging from 40 to 300 cm. Chemical formula is (Si_{11.888} Al_{0.112}) (Mg_{7.313} Al_{0.154} Fe_{0.084}) O₃₀(OH)₄(OH₂)₄ × 8H₂O. The mineral is characterized by a relatively high cation exchange capacity ranging between 240 and 360 mmol kg⁻¹ [29].
- ii) Sepiolite Sp-1 from Valdemoro (Spain) (hereafter referred as SP1), which is a reference clay from the Source Clays Repository of The Clay Minerals Society. Chemical formula is Si_{12.16} (Mg_{7.28} Al_{0.02} Fe³⁺ $_{0.02}$ Fe²⁺ $_{0.01}$) K_{0.01} O₃₀(OH)₄(OH₂)₄ × 8H₂O [31].
- iii) Fe(NO₃)₃·9H₂O acetic acid (HAc, 100%) and NaOH pellets (>99% purity) are analytical grade RPE Carlo Erba reagents.
- iv) 1,10-phenanthroline monohydrate (phen) and 1-heptanethiol (HPT) are from Sigma Aldrich.

2.2. Preparation of sepiolite- Fe^{3+} phenanthroline hybrid materials

The μ -oxo Fe³⁺phenanthroline complex (Fe³⁺phen) was obtained at pH 5.4 by preparing first 8 mM phen solution in aqueous acetate buffer

(pH = 5.4). Fe(NO₃)₃·9H₂O salt was then slowly dissolved at room temperature in the phen solution in order to have a 8 mM solution with respect to Fe³⁺ (corresponding to a 4 mM solution of iron complex, hereafter indicated as Fe³⁺phen_{pH=5.4}).

The same procedure, performed however in unbuffered solution, was used to obtain the $\rm Fe^{3+}phen$ complex solution at pH 2.3 (Fe^{3+}phen_{pH=2.3}).

Afterwards aliquots of 50 mg of sepiolite (SP1 or EB) were dispersed in 10 mL of 4 mM Fe³⁺phen_{pH = 5.4} or Fe³⁺phen_{pH=2.3} solutions and shaken for 24 h at room temperature. Solid-liquid separation was achieved via centrifugation. The same treatment was repeated three times. The separated solids were washed several times with distilled water and dried at 30 °C, to give EB-Fe³⁺phen_{pH=2.3}; EB-Fe³⁺phen_{pH=5.4}, SP1—Fe³⁺phen_{pH=2.3} and SP1—Fe³⁺phen_{pH=5.4} hybrid materials.

UV–Vis spectrophotometric measurements on the solutions resulting after adsorption and elemental analyses of the solid samples (C, N, S) were used to quantify the amount of Fe^{3+} phen adsorbed by SP1 and EB in the different working conditions.

2.3. Exposure of sepiolite- Fe^{3+} phenanthroline hybrid materials to HPT

The immobilization of HPT on EB-Fe³⁺phen_{pH=2.3}, EB-Fe³⁺phen_{pH=5.4}, SP1—Fe³⁺phen_{pH=2.3}, and SP1—Fe³⁺phen_{pH=5.4} was performed at 20 °C in a closed glass box. Approximately 60 mg of each sample were placed on the bottom of a 50mm diameter glass Petri dish and put into the glass box together with a beaker containing HPT. The HPT vapor was then allowed to reach the adsorption equilibrium within the closed glass box. After one week of exposure time, obtained samples referred as SP1-Fe³⁺phen_{pH=5.4}-HPT, $SP1 - Fe^{3+} phen_{pH=2,3} - HPT$, EB-Fe³⁺phen_{pH=5.4}-HPT, and EB-Fe³⁺ phen_{pH=23}-HPT were quantitatively characterized by elemental analysis and trapped HPT amounts were calculated from sulfur concentration.

2.4. Characterization of sepiolite and sepiolite- Fe^{3} + phenanthroline hybrid materials before and after HTP exposure

Several techniques were applied to characterize the materials.

X-ray powder diffraction (XRPD) analysis was carried out on natural sepiolite samples and after each treatment, to detect crystallographic variations on the mineral. The diffractometer used was a Philips X'Pert PRO equipped with X'Celerator detector (Cu-K α radiation, 40 kV and 40 mA; $4 \le 2\theta \le 20^\circ$, quartz as calibrating standard). The position of each peak was determined at the mid-height of the reflection, by using the software X-Pert High Score Plus.

UV–Vis measurements were recorded on a V-570 Jasco spectrophotometer. The spectrophotometer was equipped with an integrating sphere attachment (Jasco model ISN-470) and measurements were performed in the range = 220-2000 nm, by using BaSO₄ as reference.

FT-IR spectra were obtained using a JASCO FT/IR 4700 spectrophotometer (resolution: 0.4cm-1) on KBr pellets.

The elemental analyses (C, H, N, S) were performed on a Carlo Erba Model 1106 Elemental Analyser.

Thermogravimetric analyses (TGA) were performed on a Seiko SSC 5200 thermal analyser equipped with a quadrupole mass spectrometer (ESS, GeneSysQuadstar 422) that analyses gases evolved during thermal reactions (MSEGA). Gas sampling by the spectrometer was via an inert, fused silicon capillary system, heated to prevent gases condensing. Measurements were performed on each air-dried sample at the following experimental conditions: heating rate: 20.0 °C/min; heating range: 25-1000 °C; data measurement: every 0.5s; purging gas: ultrapure helium, flow rate: $100 \,\mu$ L/min. Gas analyses were carried out in Multiple Ion Detection mode (MID) which allows the qualitative deter-

mination of evolved gasses vs. temperature or time checking the intensity of the signals related to the m/z ratios 18 for H₂O, 44 for CO₂, 30 for NO and NO₂, 34 for H₂S, 46 for NO₂, and 64 for SO₂ (where m/z is the dimensionless ratio between the mass number and the charge of an ion); SEM and FARADAY detector of the spectrometer operated at 900 V with 1 s of integration time on each measured m/z signal. To avoid differences in relative humidity, samples were equilibrated for 15 min inside the oven by a 100 µL/min flow of ultrapure helium.

NMR spectra were obtained at 300 K using a an AVANCE III HD 600 Bruker spectrometer equipped with a 2.5 mm H/X CPMAS probe operating at 600.13, 156.38, and 119.22 MHz for ¹H, ²⁷Al, and ²⁹Si, respectively. Zirconia rotors of 2.5 mm o.d. were used and spun at the magic angle. ¹H NMR spectra were obtained at 33 kHz magic angle spinning (MAS) rate, using DEPTH sequence in order to remove baseline distortions [11]. The parameters used were: 125 kHz spectral width, 10 s relaxation delay, 2.4 µs 90° pulse, 4k data points and 32 scans. The empty rotor ¹H spectrum was subtracted to compensate for background effects. The cross-polarization MAS (CP-MAS) ²⁹Si NMR spectra were obtained at 8 KHz MAS rate using the standard Bruker CP sequence and a 41 kHz spectral width, 3 s relaxation delay, 2.4 µs 90° ¹H pulse, rf field strength of about 62 kHz for Hartmann-Hahn match, 3 msec contact time, 4k data points, and 512, and 5k scans for SP1, EB and EB-Fe³⁺phen_{pH=5.4}, respectively.

The ²⁷Al NMR spectra were obtained at 33 kHz MAS rates using single-pulse excitation with a 188 kHz spectral width, 2s relaxation delay, 0.5 μ s 45° pulse, 4k data points and 4k scans. All chemical shifts were referenced by adjusting the spectrometer field to the value corresponding to 38.48 ppm chemical shift for the deshielded line of the adamantane ¹³C NMR signal, as previously reported [21]. Deconvolution of ²⁹Si, ²⁷Al, and ¹H NMR spectra was obtained with MNOVA 9.1.0 software.

3. RESULTS

3.1. Elemental analysis

Elemental analyses (Table 1) have been performed on SP1 and EB natural sepiolite samples and on SP1—Fe³⁺phen_{pH=5.4}, SP1—Fe³⁺phen_{pH=2.3}, EB-Fe³⁺phen_{pH=5.4}, and EB-Fe³⁺phen_{pH=2.3} before and after HPT treatment.

Elemental analysis shows that C and N increase in sepiolite treated with Fe^{3+} phen, indicative for adsorption of the iron complex. In addition, Fe^{3+} phen is somewhat better adsorbed at pH 5.4, in particular on EB sample. The data, however, indicate that the amount of complex adsorbed by sepiolite (0.073, 0.048, 0.152, and 0.087 mol/Kg sepiolite for SP1—Fe³⁺phen_{pH=5.4}, SP1—Fe³⁺phen_{pH=2.3}, EB-Fe³⁺phen_{pH=5.4}, EB-Fe³⁺phen_{pH=2.3}, respectively) is much lower than that immobilized by montmorillonite (0.434 mol/Kg Mt).

Table 1

Mass percentage of the elements N, C, H and S for SP1 and EB natural sepiolite samples and for SP1—Fe³⁺phen_{pH=5.4}, SP1—Fe³⁺phen_{pH=2.3}, EB-Fe³⁺phen_{pH=5.4}, and EB-Fe³⁺phen_{pH=2.3} before and after HPT treatment.

Sample	N (%)	C (%)	Н (%)	S (%)
SP1	0	0.15	1.95	0
EB	0	0.46	2.52	0
SP1— $Fe^{3+}phen_{pH=5.4}$	0.41	2.05	1.81	0
SP1— $Fe^{3+}phen_{pH=2.3}$	0.27	1.41	1.93	0
$\begin{array}{l} \text{EB-Fe}^{3+} phen_{pH=-5.4} \\ \text{EB-Fe}^{3+} phen_{pH=-2.3} \\ \text{SP1} & \ \ \ \ \ \ \ \ \ \ \ \ \$	0.85	4.42	2.02	0
	0.49	2.59	2.41	0
	0.16	39.18	9.78	14.88
	0.18	23.14	5.47	8.36
	0.17	51.33	12.39	19.42
	0.23	35.50	7.81	12.99

The efficiency of the interaction HPT-sepiolite was assessed by measuring changes in sulfur content. The results show that sulfur amount strongly increases with the interaction time and EB sample treated at pH 5.4 is the most effective to reduce gaseous HPT (Table 1).

3.2. XRD analysis

Fig. 2a shows the X-ray diffraction patterns of the two starting sepiolites (SP1 and EB) in the 2θ range 5–30°. Both samples are found to be almost pure. Variation in structural ordering is a common feature in sepiolite samples of many deposits world-wide [32]. These variations can be studied through a detailed examination of the X-ray diffraction profiles.

The two diffraction tracings patterns reveal significant differences in the characteristics of diffraction reflections (i.e., in peak position, width, and relative intensity) suggesting variability both in sample crystal ordering and composition [17]. However, because of the large overlapping of reflections in the sepiolite diffraction pattern, only a few peaks can be analyzed to obtain information on the d-spacing and reflection width. The peaks that form a non-overlapping reflection are



Fig. 2. Powder diffraction patterns for the sepiolite samples. a) indexed spectrum for samples SP1 and EB; b) details of (110) variation after Fe^{3+} phen treatment for SP1. Solid line = SP1 natural sample; dotted line = $SP1-Fe^{3+}$ phen_{pH=5,4}; dashed line = SP1- Fe^{3+} phen_{pH=2,3}; c) details of (110) variation after Fe^{3+} phen treatment for EB. Solid line = EB natural sample; dotted line = EB-Fe^{3+} phen_{pH=5,4}; short dashed line = EB-Fe^{3+} phen_{pH=2,3}; solid gray line = EB treated at pH 2.3 without Fe^{3+} phen.

related to the reflections (110), (130), (131), (241), and (331). To calculate the correct position of $d_{(001)}$ and its width at half maximum (WHM) the correction procedure suggested by Sanchéz del Rio et al. [17] was applied.

Note that: i) SP1 sepiolite presents (110) reflection d-values at 12.15 Å whereas EB sepiolite at 12.0 Å; ii) all the reflections present lower intensity for EB and some of them are less defined (*e.g.*, (130), (150)), suggesting a greater disorder in EB than in SP1.

After the treatment with Fe³⁺ phen some changes in (110) peak position and shape occur, mostly evident for EB sepiolite; these variations could be attributed to modifications in the cell dimensions and in crystal order, namely: i) the $d_{(110)}$ SP1—Fe³⁺phen_{pH=5.4} and $d_{(110)}$ SP1 -Fe³⁺phen_{pH=2.3} peak positions slightly decrease up to 11.98Å (Fig. 2b); ii) the WHM of $d_{(110)}$ SP1—Fe³⁺phen_{pH=5.4} and of $d_{(110)}$ SP1— $Fe^{3+}phen_{pH=2.3}$ slightly increase from 0.62 (untreated sepiolite) to 0.64 and 0.65, respectively (Fig. 2a and b); iii) the d₍₁₁₀₎ peak position of $EB-Fe^{3+}phen_{pH=5.4}$ increases at 12.40Å and WHM increases from 0.68 (EB, natural sepiolite) to 0.99. For EB-Fe³⁺ phen_{pH=2.3} sample, the (001) reflection completely disappears and a new broad band appears in the 20 range 20–25°. To evaluate if this behavior can be related only to the acid pH value, the diffraction pattern of EB sample treated at pH = 2.3without Fe³⁺phen was collected. The result (Fig. 2c) shows evident peaks (WHM $d_{(001)} = 1.06$, $d_{(110)} = 12.40$ Å) and, consequently, acidic pH is not the only responsible for the damage of the crystalline order. Therefore, as already reported in literature [33], the modifications introduced by treatments also depend on the crystallographic features of the pristine sepiolite.

X-ray diffraction spectra obtained for samples after the HTP exposure do not indicate any further variations with respect to former samples.

3.3. DR UV-Vis measurements

The UV-Vis spectra of Fe³⁺phen in solution, obtained at different concentrations, were reported by Bernini et al. [20–22]. Fe³⁺phen spectrum is characterized by a charge transfer band (O²⁻(bridge) \rightarrow Fe³⁺ charge-transfer transition) at $\lambda = 356 \text{ nm}$ and two additional bands at 223 and 266 nm attributable to the aromatic ligand. In Fe²⁺ phen spectrum, the band at $\lambda = 356$ nm is replaced by a band with a maximum at $\lambda = 510$ nm (attributable to a d $\rightarrow \pi^*$ metal to ligand charge transfer transition) and two shoulders at $\lambda = 455$ and 493 nm [34]. The signals observed at about 356 and 510 nm will therefore be indicative of the presence of a phenanthroline complex of Fe^{3+} and Fe^{2+} , respectively. In order to confirm the interaction of Fe³⁺phen with sepiolite EB and SP1 at different pH values, the UV-Vis spectra of SP1 and EB natural samples were compared with spectra obtained for SP1-Fe³⁺phen _{pH=5.4}, SP1—Fe³⁺phen_{pH=2.3}, EB-Fe³⁺phen_{pH=5.4}, and EB Fe³⁺phen_{pH=2.3} as shown in Fig. 3. Samples SP1 and EB both display two absorbance peaks at $\lambda = 210$ and 250 nm due to electronic transitions of the mineral. After treatment with Fe³⁺phen all samples show a broadening and an overall increase in the region from $\lambda = 200-400$ nm. This increase can be associated to the presence of peaks related to the Fe³⁺phen complex. In particular the broad band with maximum at $\lambda=324\,\text{nm}$ can be assigned to the above mentioned $O^{2-}(bridge) \rightarrow Fe^{3+}$ charge-transfer transition, typical for the ferric form of the complex. All the spectra of sepiolite samples treated with Fe3+ phen and exposed to HPT show a composite band with the maximum at $\lambda = 518$ nm, also observed for Fe²⁺-phenanthroline complex in solution [22]. Also in this case, the signal corresponds to the d $\rightarrow \pi^*$ metal-to-ligand charge transfer band of the Fe²⁺-phenanthroline complex. Furthermore, the band with maximum at $\lambda = 324$ nm is no longer present in samples treated at pH = 2.3 and exposed to HPT, suggesting a complete $Fe^{3+} \rightarrow Fe^{2+}$ reduction. For EB-Fe³⁺phen_{pH=5.4}, instead, a residual broad band at about $\lambda = 324 \text{ nm}$ is still present.



Fig. 3. DR UV–Vis spectra of sepiolite and sepiolite treated with Fe^{+3} phen before and after exposure to HPT. a) SP1 sepiolite; b) EB sepiolite. Solid line: natural sample; dotted lines: samples treated with Fe^{+3} phen at pH = 2.3. The label HPT indicates curves related to samples exposed to HPT. Curves were shifted on y axis for sake of clarity.

3.4. FT-IR measurements

The FTIR spectra of natural sepiolite samples and of sepiolite-Fe³⁺phen hybrid materials before and after exposure to HPT are shown in Fig. 4. Some characteristic sepiolite bands are observed in the hydroxyl-stretching region: i) two bands at 3689 and $3620 \, \text{cm}^{-1}$ which

are associated to the symmetric stretching vibration of the OH groups coordinated with Mg^{2+} ; ii) a band at $3568 \,\mathrm{cm^{-1}}$ related to the stretching modes of H_2O molecules coordinated with octahedral Mg^{2+} cations on the channel edge; iii) two broad bands at 3363 and $3253 \,\mathrm{cm^{-1}}$ that are attributed to OH stretching vibration of differently sited zeolitic water molecules along structural channels [35,36]. The two bands at 1667 and $1619 \,\mathrm{cm^{-1}}$ can be assigned to zeolitic and adsorbed water,



Fig. 4. IR spectra of studied samples. a) SP1 sepiolite; b) EB sepiolite. Solid line: natural sample; dotted lines: samples treated with Fe^{+3} phen at pH = 5.4; dashed lines: samples treated with Fe^{+3} phen at pH = 2.3. The label HPT indicates curves related to samples exposed to HTP. Curves were shifted on y axis for sake of clarity.

respectively [37]. Bands in the 1200–400 cm⁻¹ range represent the lattice vibrations of sepiolite, i.e., the bands of Si—O—Si stretching occur at 1021 cm⁻¹, the band at 979 cm⁻¹ forms as a result of stretching vibration of Si—O—Si bonds connected by non-linear bridge oxygen [38], whereas the band at 956 cm⁻¹ is related to terminal Si—OH deformation. Effects at 486 and 503 cm⁻¹ (shoulder) can be attributed to an O— Si—O bending, whereas those at 643 and 691 cm⁻¹ result from Mg— OH bending mode vibrations. For EB sample the bands at 3689 and at 3619 cm⁻¹ appear less enhanced. This behavior can suggest octahedral substitutions and/or vacancies [36].

In the IR spectra obtained after the immobilization of Fe³⁺ phen complex (SP1—Fe³⁺phen_{pH=5.4}, SP1—Fe³⁺phen_{pH=2.3}, EB-Fe³⁺phen_{pH=2.3}, and EB-Fe³⁺phen_{pH=2.3}) the following changes are observed: i) a broad shoulder in the 3200–2900 cm⁻¹ range, more evident in EB-Fe³⁺phen_{pH=2.3} spectrum, that can be assigned to ν (CH) bands of the phenanthroline moieties; ii) a decrease in the adsorption bands in the 4000–3000 cm⁻¹ range, probably suggesting that some water molecules leave partially the sepiolite structure after Fe³⁺phen addition. This feature could also suggest structural variation of sepiolite or that Fe³⁺phen molecules replace some water molecules coordinated to Mg²⁺; iii) the band at 1212 cm⁻¹ and the shoulder at 1194 cm⁻¹, that indicate changes in sepiolite structural order [39], do not show evident changes with respect to those observed for untreated sample; v) the OH bending effect at 1654 cm⁻¹ decreases its intensity, probably suggesting changes in zeolitic-water bonding.

Analyzing comparatively the spectra of the samples after HPT exposition the following changes are observed: i) four new bands at 2955, 2926, 2871, and 2855 cm⁻¹ which can be related to C—H stretching of heptanethiol interacting with Fe³⁺phen treated sepiolite. The bands at 2871 and 2855 cm⁻¹ can be assigned to the symmetric stretching vibrations of CH₃ and CH₂, whereas those at 2955 and 2926 cm⁻¹ to the antisymmetric stretching vibrations of CH₃ and CH₂ groups, respectively [40,41]; weak bending signals of heptanethiol can be observed: the scissoring of CH₂ at about 1465 cm⁻¹, the antisymmetric and symmetric bending of CH₃ at 1457 and at 1378 cm⁻¹, respectively; ii) the transmittance of the band in the 4000–3000 cm⁻¹ range decreases, suggesting the water molecules leave partially the sepiolite structure.

No band associated with the S—H stretching vibration (sharp and weak signals at $2550-2600 \text{ cm}^{-1}$) is observed.

3.5. Thermal analysis

Thermogravimetric analyses (TGA) together with the derivative signal (DTGA) are shown in Fig. 5.

The thermal behavior of natural sepiolite samples is here briefly summarized. In the temperature range 30-600 °C, both samples indicate three distinct weight loss steps with maxima below $100^{\circ}C$ (SP1 = 93 °C; EB = 80 °C), between 250 and 350 °C (SP1 = 315 °C; EB = 302 °C), and between 350 and 600 °C (SP1 = 535 °C; EB = 513 °C). The first endothermic effect with mass loss (wt%) of 11.90% (SP1) and 10.07% (EB) is due to the loss of hygroscopic and zeolitic H₂O; the second peak with mass loss of 3.18% (SP1) and 3.74% (EB) is due to the loss of part of the structural H₂O. The release of structural H₂O continues up to 600 °C (wt%: SP1 = 2.49%; EB = 3.28%). After the second dehydration step the complete collapse of sepiolite channels occurs [4,14]. At higher temperature values SP1 shows a well-defined effect at 835 °C (wt% = 2.35) whereas sample EB evidences three broad effects at about 737, 797, and 815 °C (overall wt% = 4.30). This different behavior can be possibly associated either to tetrahedral and octahedral substitutions that are more frequent in EB sample with respect to SP1 sample, or to the different morphology with EB showing greater variability in fibres dimensions with respect to the larger and more regular ones observed in SP1, as indicated in literature [17] and confirmed by our XRPD data. These endothermic reactions, related to dehydroxylation, transform sepiolite into the amorphous phase meta-sepiolite [42]. The exothermic peak at 843 and 822 °C in SP1 and EB, respectively (observed in differential thermal curves and not graphically reported here), is attributed to the re-crystallization of the dehydroxylated phase and to the formation of enstatite (MgSiO₃). The evolved gas during thermal analysis (MSEGA), are all related to the dehydration or dehydoxylation relations (release of H₂O, m/z = 18, Figs. 6 and 7).

In the thermal range 25-600°C, the DTGA (Fig. 5a and b) and MSEGA (Figs. 6 and 7) curves of SP1-Fe³⁺phen_{pH=5.4}, SP1- $Fe^{3+}phen_{pH=2.3}$, EB-Fe³⁺phen_{pH=5.4}, and EB-Fe³⁺phen_{pH=2.3} show: i) a well-defined thermal reaction at about 65°C, related to H₂O release only (m/z = 18), associated with a weight loss much lower than in pristine $Fe^{3+}phen_{pH=2.3} = 3.85 wt\%,$ EB-Fe³⁺phen_{pH=2.3} = 2.21 wt%); ii) a reaction at about 270 °C, more precisely: $SP1 - Fe^{3+}phen_{pH=5.4} = 295 \degree C$ (wt% = 4.03), $SP1 - Fe^{3+}phen_{pH=2.3} = 281 \degree C$ (wt% = 3.78), $EB-Fe^{3+}phen_{pH=5.4} = 263 \degree C$ (wt% = 5.06), and EB-Fe³⁺phen_{pH=2.3} = 265 °C (wt% = 4.27), which is related to the release of H_2O (m/z = 18) and NO (m/z = 30); iii) an effect with maximum in the temperature range between 440 and 480 °C $(\text{SP1}-\text{Fe}^{3+}\text{phen}_{\text{pH}=5.4} = 448 \,^{\circ}\text{C}$ (wt% = 5.45.19),SP1- $Fe^{3+}phen_{pH=2.3} = 446$ °C (wt% = 4.91), EB-Fe³⁺phen_{pH=5.4} = 472 °C (wt% = 7.51), and EB-Fe³⁺ phen_{pH=2.3} = 474 °C (wt% = 7.16) mostly associated to the release of NO (m/z = 30) and CO₂ (m/z = 44) and by residual H_2O molecules (m/z = 18); iv) in the temperature range between 600 and 1000 $^\circ C$ in SP1—Fe^{3+}phen_{pH=5.4} and SP1— $Fe^{3+}phen_{pH=2.3}$ the band observed at 835 °C in pristine sepiolite enlarge and the maximum shifts at about 770°C (SP1- $Fe^{3+}phen_{pH=5.4} = 5.18 \text{ wt\%}; \text{ SP1}-Fe^{3+}phen_{pH=2.3} = 5.38 \text{ wt\%}) \text{ and is}$ associated to H₂O (m/z = 18), NO (m/z = 30), and CO₂ (m/z = 44) release; v) EB-Fe³⁺phen_{pH=5.4} and EB-Fe³⁺phen_{pH=2.3} show a well-depeak at T = 680 °C $(EB-Fe^{3+}phen_{pH=5.4} = 7.11 \text{ wt}\%;$ fined EB-Fe³⁺ phen_{pH=2.3} = 4.85 wt%) mostly related to CO₂ (m/z = 44) loss, and two broad effects between 720 and 1000°C characterized by 4.63 wt% (EB-Fe³⁺phen_{pH=5.4}) and 6.31 wt% (EB-Fe³⁺phen_{pH=2.3}) associated with H₂O (m/z = 18), NO (m/z = 30), and CO₂ (m/z = 44) release.

After the HPT exposure the overall weight loss strongly increases for all samples (SP1—Fe³⁺phen_{pH=5.4} = 64.12 wt%; SP1— Fe³⁺phen_{pH=2.3} = 47.3 wt%; EB-Fe³⁺phen_{pH=5.4} = 62.5 wt%, and EB-Fe³⁺phen_{pH=2.3} = 50.0 wt%), being mostly related to SO₂ release at about 200 °C (Figs. 6 and 7).

No release of H_2S (m/z = 34) and NO_2 (m/z = 46) was observed in the investigated thermal range.

3.6. NMR analysis

Fig. 8 compares the CP-MAS ²⁹Si NMR spectra of samples SP1 and EB. Three major signals at -97.2, -94.2, and -91.7 ppm, corresponding to type 1 (edge), 3 (centre), and 2 (near edge) Si sites, respectively, are present [25]. A fourth resonance at -85.2 ppm, low in SP1, is clearly detected in EB sepiolite sample. It has been assigned to Q² ²⁹Si—OH nuclei [43] and indicates the presence of a higher number of these sites in EB with respect to SP1.

Moreover, ²⁹Si signals are broader in EB and deconvolution shows that this broadness could be due to a broad component at about -96 ppm (Fig. SM1). This points to a certain distortion of the structure of EB sepiolite with respect to SP1.

The ${}^{27}\text{Al}$ NMR spectra of EB and SP1 are reported in Fig. 9 and are quite different. In SP1 the majority of Al³⁺ ions are found in octahedral sites, and only about 25% in tetrahedral ones, whereas in EB 2:3 Al³⁺ ions are found in tetrahedral sites (Fig. SM2). Two of them are distinguished at 67.7 and 58.9 ppm and the former is absent in SP1.



Fig. 5. Thermal analyses of sepiolite samples. a and b: sample SP1; c and d: sample EB. Plots a and c report TGA curves; plots b and d the DTGA curves. Solid line: natural samples; dotted lines: samples treated with Fe⁺³phen at pH = 5.4; dashed lines: samples treated with Fe⁺³phen at pH = 2.3. The label HTP indicates curves of samples exposed to HPT. DTGA curves were shifted on y axis for sake of clarity.

The deshielded chemical shift of this signal can be related to a distortion of the corresponding O-AI-O bond angles (the higher the bond angle the higher the chemical shift) [44]. ²⁹Si and ²⁷Al data are resumed in Table 2.

4. DISCUSSION

The interaction of Fe^{3+} phen with sepiolite is influenced by the mineral crystal order. SP1 shows a higher crystal order than EB, as demonstrated by narrower peaks in the X-ray spectra. When treated with Fe^{3+} phen, the two samples show different binding efficiency, with EB demonstrating a significant higher adsorption capacity at the same treatment conditions. Adsorption is also favored in both samples at pH 5.4 when compared to pH 2.3. At this lower pH value long-range struc-

tural order of EB sample is strongly compromised, as demonstrated by the absence of peaks in XRD spectra.

Treatment with Fe^{3+} phen reduces the amount of hygroscopic and zeolitic water in both samples. For natural SP1 and EB samples, thermogravimetric analyses show water release below 100 °C of 11.9 and 10.07 wt%, respectively. After Fe^{3+} phen treatment, this process is observed at lower temperature and is associated to a decrease of the weight loss amount, i.e. 3.85 and 2.21 wt% at pH 2.3 and 6.18 and 3.83 wt% at pH 5.4 for SP1 and EB, respectively. All these data suggest that a more efficient adsorption process is associated to a lowering in hygroscopic and zeolitic water content present in the treated sample. The decrease of hygroscopic and zeolitic water following Fe^{3+} phen treatment is also confirmed by NMR data, revealing also an effect over the feature associated to Mg—OH and Si—OH moieties (Figs. SM3-SM5).



Fig. 6. Evolved gasses mass analyses (H_2O , m/z = 18; NO, m/z = 30; CO₂, m/z = 44, and SO₂, m/z = 64) reported as a function of temperature for SP1 sepiolite sample. Solid line: natural sample; dotted lines: samples treated at pH = 5.4; dashed lines: samples treated at pH = 2.3. The label HTP indicates curves of samples exposed to HPT. Curves were shifted on y axis for sake of clarity.

IR spectra (Fig. 4 and SM7) show a variation at 3688 cm^{-1} in Fe³⁺phen-treated samples. This modification can be attributed to the OH groups involved in the Mg²⁺—OH symmetric stretching vibrations [45]. All these data are consistent with Fe³⁺phen location not only on the external surface of the mineral, but also on the channels hosting zeolitic water. In this case, the Fe³⁺phen aromatic rings within sepiolite channels should be very close to the structural hydroxyl protons of sepiolite, as also inferred from NMR results (Fig. SM3).

As already found for montmorillonite, the exposure of samples treated with Fe^{3+} phen to HTP does not induce significant modification of layer structure as evidenced by XRPD data, but rather remarkable ef-

fects on pristine Fe³⁺phen, with reduction of Fe³⁺ to Fe²⁺ [22]. Fe³⁺ to Fe²⁺ reduction is likely associated with the oxidation of thiol to disulfide in a redox pathway. After that, the resulting Fe²⁺ phen rapidly binds a first thiolate ion and, possibly, a second one, according to the following mechanism in which coordinated H₂O molecules are omitted for clarity sake [22]:

$$[\text{phenFe}^{3+} - \text{O} - \text{Fe}^{3+}\text{phen}]^{4+} + 2 \text{ RSH}$$

$$\rightarrow 2 [\text{phenFe}]^{2+} + \text{RS} - \text{SR} + \text{H}_2\text{O}$$
(1)



Fig. 7. Evolved gasses mass analyses (H_2O , m/z = 18; NO, m/z = 30; CO₂, m/z = 44, and SO₂, m/z = 64) reported as a function of temperature for EB sepiolite sample. Solid line: natural sample; dotted lines: samples treated at pH = 5.4; dashed lines: samples treated at pH = 2.3. The label HTP indicate curves of samples exposed to HTP. Curves were shifted on y axis for sake of clarity.



Fig. 8. ²⁹Si CP-MAS NMR spectra of SP1 and EB.



$$2 \left[\text{phenFe} \right]^{2+} + 2 \text{ RSH} \rightarrow 2 \left[\text{phenFe}^{2+} \text{SR} \right]^{+} + 2 \text{H}^{+}$$
(2)

$$2 [phenFe^{2+}SR]^{+} + 2 RSH
\rightarrow 2 [phenFe^{2+}(SR)_{2}] + 2 H^{+}(3)$$
(3)

corresponding to the overall reaction:

$$[phen - Fe^{3+} - O - Fe^{3+}phen]^{4+} + 6 RSH$$

$$\rightarrow RS - SR + 2 [phenFe^{2+}(SR)_2] + H_2O + 4H^+$$
(4)

Thiol is not physi-adsorbed into sepiolite structure, as evidenced by the absence in IR spectra (Fig. 4) of the typical signal related to S-H stretching (2550–2600 cm⁻¹) that should otherwise be present.

Both Fe³⁺phen-treated montmorillonite and sepiolite can thus be used, at room temperature, for removal of thiols present in gas phases. Sepiolite is, however, definitely more effective, as demonstrated by a sulfur content in the reaction products significantly greater than in montmorillonite, although the amount of iron complex adsorbed per unit of mass of sepiolite is extremely less than that immobilized by montmorillonite. In fact, sulfur content in sepiolite SP1 is 8.36% (pH = 2.3) and 14.88% (pH = 5.4), while in sepiolite EB is 12.99% (pH = 2.3) and 19.42% (pH = 5.4). In montmorillonite sulfur content is 5.2% and is independent on pH value. The total thiol immobilized by montmorillonite treated with Fe³⁺phen is the stoichiometric one, corresponding to 3 thiol molecules per iron. The fact that the Fe³⁺phen complex immobilized on sepiolite leads to thiol immobilization in much higher quantities than obtained on montmorillonite suggests the presence of a catalytic oxidation mechanism of thiol superimposed on the above mechanism ((1)-(3)). In fact in montmorillonite treated with Fe³⁺phen the limit value of the molar ratio S/Fe is 3 [22], while for SP1 at pH 2.3 and 5.4 it is 40 and 81, respectively, and for EB at pH 2.3 and 5.4 it is 49 and 99, respectively. Nevertheless, we can not exclude that the larger space availability for thiol inside sepiolite channels with respect to montmorillonite interlayer which is filled by strongly intercalated complex molecules could be a further reason for the higher sulfur storage in sepiolite with respect to montmorillonite.

5. CONCLUSIONS

Fe³⁺phen complex, immobilized on mineral surfaces, is extremely effective as a gas trap for thiols; its efficiency, however, is strongly conditioned by the nature of the interacting surface (or interlayer). This complex adsorbed on sepiolite is able to catch much higher amounts of thiol than the stoichiometric one, probably through a catalytic oxidation mechanism that, conversely, does not occur when Fe³⁺phen is intercalated in montmorillonite. The efficiency of this catalytic process, in turn, is significantly affected by the structural features of sepiolite and by pH, as evidenced by the fact that sepiolite EB works better than sepiolite SP1 and thiol removal is larger at pH 5.4 with respect to pH 2.3. The optimization of an immobilization process of an active chemical species on a mineral surface, therefore, should involve also the tun-

Table 2

²⁹Si^a and ²⁷Al chemical shifts (ppm) of SP1 and EB sepiolite samples. See Figs SM5-SM6 for further details.

Sample	Q ^{2 29} Si—ОН	Q ^{3 29} Si(1)	Q ^{3 29} Si(2)	Q ^{3 29} Si(3)	M ^{b27} Al	T(1) ^{b27} Al	T(2) ^{b27} Al
SP1	-85.1	-97.8	-91.7	-94.2	5.7	58.4	nd
EB	-85.2	-97.8	-91.8	-94.2	6.1	58.9	67.7

^a Labeled as in Raya et al. (2010) [25].

 b M = octahedral sites, T = tetrahedral sites (Smith, 1993) [44].

ing of the physico-chemical and structural properties of the surface itself.

ACKNOWLEDGMENTS

Financial support was provided under grants "FFABR (Fondo Finanziamento Attività Base di Ricerca, legge 232/2016)" and "FAR-UNI-MORE 2016 PASTIME". An appreciated support was also provided by Centro Interdipartimentale Grandi Strumenti (CIGS) of Università di Modena e Reggio Emilia and by its staff. Thanks are also due to Fondazione Cassa di Risparmio di Modena for supporting the acquisition of the Bruker 600 MHz NMR spectrometer.

Appendix A. Supplementary data

Supplementary data to this article can be found online at https://doi.org/10.1016/j.micromeso.2019.04.054.

Appendix

Additional information on materials characterization are reported in the Supplementary Materials. Figs. SM1-SM6 report additional data related to NMR spectroscopy (i.e., the deconvolution of CPMAS ²⁹Si (Fig. SM1) and ²⁷Al (Fig. SM2) NMR spectra of natural sepiolites, the ¹H NMR spectra of EB-Fe³⁺phen and EB (Fig. SM3), the deconvolution of ¹H NMR spectra of EB-Fe³⁺phen and EB (Fig. SM4), the CP-MAS ²⁹Si NMR spectrum of EB-Fe³⁺phen (Fig. SM5), and the ²⁷Al NMR spectra of EB-Fe³⁺phen and EB (Fig. SM7 reports an expansion of the IR spectra in the wave number range 3800–3500.

References

- E. Galan, Clay Miner. 31 (1996) 443–453, https://doi.org/10.1180/claymin.1996. 031.4.01.
- [2] M.F. Brigatti, D. Malferrari, A. Laurora, C. Elmi, in: M.F. Brigatti, A. Mottana (Eds.), Layered Mineral Structures and Their Application in Advanced Technologies, EMU Notes in Mineralogy, 2011, pp. 1–71.
- [3] K. Brauner, A. Preisinger, Tschermaks Mineral. Petrogr. Mittl. 6 (1956) 120–140.
 [4] J.E. Post, D.L. Bish, P.J. Heaney, Am. Mineral. 92 (2007) 91–97, https://doi.org/
- [4] J.E. Post, D.L. Bish, P.J. Heaney, An. Mineral. 92 (2007) 91–97, https://doi.org/ 10.2138/am.2007.2134.
- [5] F. Zhou, C.J. Yan, Y. Zhang, J.J. Tan, Appl. Clay Sci. 125 (2016) 119–126 https:// doi.org/10.1016/j.clay.2016.02.013.
- [6] E. Ruiz-Hitzky, J. Mater. Chem. 11 (2001) 86–91, https://doi.org/10.1039/ B003197F.
- [7] F. Muniz-Miranda, F. Lodesani, F. Tavanti, D. Presti, D. Malferrari, A. Pedone J, Phys. Chem. C 120 (2016) 26945–26954, https://doi.org/10.1021/acs.jpcc. 6b09983.
- [8] Q.K. Wang, T. Matsuura, C.Y. Feng, M.R. Weir, C. Detellier, R.L. Rutadinka, R.L. Van Mao, J. Membrane Sci 184 (2001) 153163 https://www.cheric.org/research/ tech/periodicals/doi.php?art_seq=309285.
- [9] R. Giustetto, K. Seenivasan, S. Bordiga, Period. Mineral. (2010) 21–37, https://doi. org/10.2451/2010PM0019.
- [10] R. Giustetto, D. Levy, O. Wahyudi, G. Ricchiardi, J.G. Vitillo, Eur. J. Mineral. 23 (2011) 449–466 https://doi.org/10.1127/0935-1221/2011/0023-2105.
- [11] R. Giustetto, K. Seenivasan, F. Bonino, G. Ricchiardi, S. Bordiga, M.R. Chierotti, R. Gobetto, J. Phys. Chem. C 115 (2011) 16764–16776, https://doi.org/10.1021/ jp203270c.
- [12] W. Kuang, G.A. Facey, C. Detellier, J. Mater. Chem. 16 (2006) 179–185, https:// doi.org/10.1039/B512575H.

- [13] R. M Mamdoh, M.R. Ghada, M. Essam, A.S. Ebtissam, M.E. Ahmed, Appl. Clay Sci. 141 (2017) 72–80 https://doi.org/10.1016/j.clay.2016.12.021.
- [14] S. Ovarlez, F. Giulieri, A.M. Chaze, F. Delamare, J. Raya, J. Hirschinger, Chem. Eur J. 15 (2009) 11326–11332 https://doi.org/10.1002/chem.200901482.
- [15] E. Sabah, M.S. Çelik, J. Colloid Interface Sci. 251 (2002) 33–38 https://doi.org/10. 1006/jcis.2002.8394.
- [16] J. Weng, Z. Gong, L. Liao, G. Lv, J. Tan, Appl. Clay Sci. 161 (2018) 505–512, https: //doi.org/10.1016/j.clay.2018.05.018.
- [17] M. Sánchez del Río, E. García-Romero, I. Suárez, M. da Silva, L. Fuentes-Montero, G. Martínez-Criado, Am. Mineral. 96 (2011) 1443–1454, https://doi.org/10.2138/ am.2014.4751.
- [18] M. Alvarado Jr., R.C. Chianelli, R.M. Arrowood, Bioinorgan. Chem. Appl. (2012) 672562 https://doi.org/10.1155/2012/672562.
- [19] D. Karataş, A. Tekin, M.S. Çelik, Clay Clay Miner. 65 (2017) 1–13, https://doi.org/ 10.1346/CCMN.2016.064043.
- [20] F. Bernini, E. Castellini, D. Malferrari, M. Borsari, M.F. Brigatti, Microporous Mesoporous Mater. 211 (2015) 19–29, https://doi.org/10.1016/j.micromeso.2015.02. 039.
- [21] E. Castellini, F. Bernini, M. Borsari, M.F. Brigatti, G.R. Castro, D. Malferrari, L. Medici, A. Mucci, Clay Clay Miner. 65 (2017) 220–233, https://doi.org/10.1346/ CCMN.2017.064065.
- [22] F. Bernini, E. Castellini, D. Malferrari, G.R. Castro, C.I. Sainz-Díaz, M.F. Brigatti, M. Borsari, Applied Materials Interfaces 9 (2017) 1045–1056, https://doi.org/10. 1021/acsami.6b11906.
- [23] D. Malferrari, E. Castellini, F. Bernini, A. Serrano Rubio, G.R. Castro, C.I. Sainz-Díaz, M. Caleffi, M.F. Brigatti, M. Borsari, Microporous Mesoporous Mater. 265 (2018) 8–17 https://doi.org/10.1016/j.micromeso.2018.01.017.
- [24] R. Sui, S.K. Carefoot, C.B. Lavery, C.E. Deering, K.L. Lesage, N. Chou, C.J. Rose, R.A. Marriott, J. Mat.s Chem. A 5 (2017) 9561–9571, https://doi.org/10.1039/ C7TA01856H.
- [25] J. Raya, J. Hirschinger, S. Ovarlez, F. Giulieri, A.M. Chaze, F. Delamare, Phys. Chem. Chem. Phys. 43 (2010) 14508–14514, https://doi.org/10.1039/ c0cp00834f.
- [26] M.F. Brigatti, C.I. Sainz Diaz, M. Borsari, F. Bernini, E. Castellini, D. Malferrari, Rend. Fis. Acc. Lincei (2017) https://doi.org/10.1007/s12210-017-0615-1.
- [27] A. Alietti, M.F. Brigatti, L. Poppi, Rend. Soc. It. Miner. Petrol. 39 (1984) 163–172.
- [28] K. Stahr, M. Zarei, R. Jahn, Mittl. Dtsch. Bodenkd. Ges. 62 (1990) 147–150.
- [29] A. Singer, K. Stahr, M. Zarei, Clay Miner. 33 (1998) 349-362.
- [30] A.M.A. Gure, Bristol, UK: Sunlight Water and Environmental Consultancy Services, 2015.
- [31] C. He, E. Makovicky, B. Osbaeck, Appl. Clay Sci. 10 (1996) 337–349 https://doi. org/10.1016/0169-1317(95)00035-6.
- [32] E. Galán, M. Pozo (Eds.), Palygorskite and sepiolite deposits in continental environments. Description, genetic patterns and sedimentary settings. Development of Clay Science, 3, Elsevier, 2011, pp. 125–173, 978-0-444-53607-5.
- [33] F. Franco, M. Pozo, J.A. Cecilia, M. Benítez-Guerrero, E. Pozo, J.A. Martín Rubí, Appl. Clay Sci. 102 (2014) 15–27 https://doi.org/10.1016/j.clay.2014.10.013.
- [34] W.R. McWhinnie, J.D. Miller, The Chemistry of Complexes Containing 2,2'-Bipyridyl, 1,10-phenanthroline or 2,2',6',2''-Terbipyridyl as ligands, In: H.J. Hemeléus, A.G. Sharpe (Eds.), Advances in Inorganic Chemistry and Radiochemistry. vol. 12. Academic Press. New York. 1961, p. 163.
- [35] R.L. Frost, O.B. Locos, H. Ruan, J.T. Kloprogge, Vib. Spectrosc. 27 (2001) 1-13.
- [36] R.L. Frost, G.A. Cash, J.T. Kloprogge, Vib. Spectrosc. 16 (1998) 173-184.
- [37] V.C. Farmer, The layer silicates, in: V.C. Farmer (Ed.), The Infrared Spectra of Minerals, Mineralogical Society, London, 1974, pp. 331–363, Monogra ph 4.
- [38] A.M. Sevim, R. Hojiyev, A. Gül, M.S. Celik, Dyes Pigments 88 (2011) 25–38, https: //doi.org/10.1016/j.dyepig.2010.04.011.
- [39] M. Pozo, J.P. Calvo, E. Pozo, A. Moreno, Appl. Clay Sci. 91–92 (2014) 30–45 https: //doi.org/10.1016/j.clay.2014.02.005.
- [40] L. Bertilsson, R. Liedberg, B., Langmuir 9 (1993) 141-149.
- [41] T. M Uehara, H.B. de Aguiar, K. Bergamaski, P.B. Miranda, J. Phys. Chem. C 118 (2014) 20374–20382, https://doi.org/10.1021/jp5054919.
- [42] N. Yener, M. Önal, G. Üstünişik, Y. Sarıkaya, J. Therm. Anal. Calorim. 88 (2007) 813–817 https://doi.org/10.1007/s10973-005-7459-0.
- [43] M.R. Weir, W. Kuang, G.A. Facey, C. Detellier, Clay Clay Miner. 51 (2003) 318–326, https://doi.org/10.1346/CCMN.2003.0510308.
- [44] M.E. Smith, Appl. Magn. Reson. 4 (1993) 1-64.
- [45] G. Rytwo, S. Nir, L. Margulies, B. Casal, J. Merino, E. Ruiz-Hitzky, J.M. Serratosa, Clay Clay Miner. 46 (1998) 340–348.