

(12) **United States Patent**
Iucolano et al.

(10) **Patent No.:** **US 10,892,357 B2**
(45) **Date of Patent:** ***Jan. 12, 2021**

(54) **DOUBLE-CHANNEL HEMT DEVICE AND MANUFACTURING METHOD THEREOF**

(58) **Field of Classification Search**
None
See application file for complete search history.

(71) Applicant: **STMICROELECTRONICS S.R.L.**,
Agrate Brianza (IT)

(56) **References Cited**

(72) Inventors: **Ferdinando Iucolano**, Gravina di
Catania (IT); **Alessandro Chini**,
Modena (IT)

U.S. PATENT DOCUMENTS

6,274,893 B1 8/2001 Igarashi et al.
6,521,961 B1 2/2003 Costa et al.

(73) Assignee: **STMICROELECTRONICS S.r.l.**,
Agrate Brianza (IT)

(Continued)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

FOREIGN PATENT DOCUMENTS

CN 102130158 A 7/2011
CN 102629624 A 8/2012

This patent is subject to a terminal dis-
claimer.

(Continued)

OTHER PUBLICATIONS

(21) Appl. No.: **16/431,642**

Bisi et al., "Kinetics of Buffer-Related R_{ON} —Increase in GaN-on-Silicon MIS-HEMTs," *IEEE Electron Device Letters* 35(10): 1004-1006, 2014.

(22) Filed: **Jun. 4, 2019**

(Continued)

(65) **Prior Publication Data**

US 2019/0288100 A1 Sep. 19, 2019

Primary Examiner — Khaja Ahmad

Related U.S. Application Data

(74) *Attorney, Agent, or Firm* — Seed IP Law Group LLP

(63) Continuation of application No. 15/393,945, filed on
Dec. 29, 2016, now Pat. No. 10,381,470.

(57) **ABSTRACT**

An HEMT device, comprising: a semiconductor body including a heterojunction structure; a dielectric layer on the semiconductor body; a gate electrode; a drain electrode, facing a first side of the gate electrode; and a source electrode, facing a second side opposite to the first side of the gate electrode; an auxiliary channel layer, which extends over the heterojunction structure between the gate electrode and the drain electrode, in electrical contact with the drain electrode and at a distance from the gate electrode, and forming an additional conductive path for charge carriers that flow between the source electrode and the drain electrode.

(30) **Foreign Application Priority Data**

May 30, 2016 (EP) 16425047

20 Claims, 6 Drawing Sheets

(51) **Int. Cl.**


H01L 29/778 (2006.01)
H01L 29/66 (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC **H01L 29/7787** (2013.01); **H01L 21/0254**
(2013.01); **H01L 21/02458** (2013.01);

(Continued)



- (51) **Int. Cl.**
H01L 29/06 (2006.01)
H01L 21/02 (2006.01)
H01L 29/20 (2006.01)
H01L 29/205 (2006.01)
H01L 29/40 (2006.01)
H01L 29/417 (2006.01)
H01L 29/423 (2006.01)

CN 102683406 A 9/2012
 JP 2001-127282 A 5/2020

OTHER PUBLICATIONS

Chevtchenko et al., "Off-state breakdown and dispersion optimization in AlGa_N/Ga_N heterojunction field-effect transistors utilizing carbon doped buffer," *Applied Physics Letters* 100:223502, 3 pages, 2012.

Hilt et al., "Normally-off Ga_N Transistors for Power Applications," *Journal of Physics: Conference Series* 494:012001, 6 pages, 2014.

Hwang et al., "Impact of Channel Hot Electrons on Current Collapse in AlGa_N/Ga_N HEMT's," *IEEE Electron Device Letters* 31(12): 1494-1496, 2013.

Jin et al., "Total current collapse in High-Voltage Ga_N MIS-HEMTs induced by Zener trapping," *IEEE, Microsystems Technology Laboratories, Massachusetts Institute of Technology*, pp. 6.2.1-6.2.4, 2013.

Lin, "Market and Technology Trends in WBG Materials for Power Electronics Applications," CS Mantech Conference, May 18-21, 2015, Scottsdale, Arizona, USA pp. 33-36.

Moens et al., "On the Impact of Carbon-Doping on the Dynamic Ron and Off-state Leakage Current of 650V Ga_N Power Devices" 2015 IEEE 27th International Symposium on Power Semiconductor Devices & IC's (ISPSD), 2015, 4 pages.

Würlf et al., "Techniques towards Ga_N power transistors with improved high voltage dynamic switching properties," *IEDM13-147* pp. 6.1.1-6.1.4, 2013.

- (52) **U.S. Cl.**
 CPC **H01L 29/0657** (2013.01); **H01L 29/2003** (2013.01); **H01L 29/205** (2013.01); **H01L 29/402** (2013.01); **H01L 29/66462** (2013.01); **H01L 29/66522** (2013.01); **H01L 29/7786** (2013.01); **H01L 29/41766** (2013.01); **H01L 29/4236** (2013.01); **H01L 29/42376** (2013.01)

(56) **References Cited**

U.S. PATENT DOCUMENTS

9,419,121 B1* 8/2016 Teo H01L 29/41758
 2007/0278518 A1 12/2007 Chen et al.
 2014/0159116 A1* 6/2014 Briere H01L 29/402
 257/194
 2017/0092752 A1* 3/2017 Lu H01L 29/66462

FOREIGN PATENT DOCUMENTS

CN 102637726 A 8/2012

* cited by examiner




Fig. 1




Fig. 2




Fig.3




Fig.4




Fig. 5




Fig. 6A




Fig.6B




Fig.6C




Fig.6D




Fig.6E




Fig.7

DOUBLE-CHANNEL HEMT DEVICE AND MANUFACTURING METHOD THEREOF

BACKGROUND

Technical Field

The present disclosure relates to an HEMT device and to a method for manufacturing the same.

Description of the Related Art

Known to the art are high-electron-mobility transistors (HEMTs) with heterostructure made, in particular, of gallium nitride (GaN) and aluminum gallium nitride (AlGaN). For example, HEMT devices are appreciated for use as power switches thanks to their high breakdown threshold. In addition, the high current density in the conductive channel of the HEMT enables a low ON-state resistance (RON) of the conductive channel.

In order to favor use of HEMTs in high-power applications, recessed-gate HEMTs have been introduced.

A problem with devices of this type regards the drastic reduction of current, due to an increase of the ON-state resistance (Rory), during switching operations. The temporary increase in the RON value after high-voltage biasing (400-600 V) in the OFF state is deemed to be caused by an excessive trapping of the charge carriers in the channel, in the buffer layer, or at the surface.

In order to reduce this problem, various solutions have been adopted.

The document by D. Jin et al., "Total current collapse in High-Voltage GaN MIS-HEMTs induced by Zener trapping", Microsystems Technology Laboratories, Massachusetts Institute of Technology, Cambridge, Mass., U.S.A., represents a method of control of defects during the stage of epitaxial growth of the channel and an appropriate design of the "field plate" structures. This method, however, does not solve the problem and requires a control of the growth stage, which has an impact on the costs of industrial production of HEMTs.

The document by P. Moens et al., "On the Impact of Carbon-Doping on the Dynamic Ron and Off-state Leakage Current of 650V GaN Power Devices", ON Semiconductor, suggests that the optimization of the doping profile with carbon atoms of the semiconductor body of the HEMT at the level of the buffer layer may provide a solution to the aforementioned problem. However, the presence itself of impurities such as carbon atoms may itself be the cause of further trapping of carriers and Rory degradation.

The document by J. Würfl et al., "Techniques towards GaN power transistors with improved high voltage dynamic switching properties", 2013, discusses the limitation of dynamic switching in a GaN power device and proposes techniques for improving fast switching at high voltage by modifying the structure of the buffer layer of an HEMT. The aforementioned problems, however, are not solved.

BRIEF SUMMARY

At least some embodiments of the present disclosure provide an HEMT device and a manufacturing method thereof that are alternative to the ones proposed according to the prior art, and that overcome the drawbacks set forth above.

According to at least one embodiment of the present disclosure, an HEMT device includes:

a semiconductor body including a heterojunction structure that forms a main conductive channel of the HEMT device;

a dielectric layer on the semiconductor body;

a gate electrode, a drain electrode, and a source electrode aligned with one another in a direction, wherein the drain electrode extends facing a first side of the gate electrode, and the source electrode extends facing a second side, opposite to the first side in said direction, of the gate electrode; and an auxiliary channel layer, which extends over the heterojunction structure between the gate electrode and the drain electrode, is in electrical contact with the drain electrode, is spaced apart from the gate electrode, and forms a conductive path additional to the main conductive channel for charge carriers that flow between the source electrode and the drain electrode.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

For a better understanding of the present disclosure, preferred embodiments thereof are now described, purely by way of non-limiting example and with reference to the attached drawings, wherein:

FIG. 1 shows, in lateral sectional view, an HEMT device according to one embodiment of the present disclosure;

FIG. 2 shows, in lateral sectional view, an HEMT device according to a further embodiment of the present disclosure;

FIG. 3 shows, in lateral sectional view, an HEMT device according to a further embodiment of the present disclosure;

FIG. 4 shows, in lateral sectional view, an HEMT device according to a further embodiment of the present disclosure;

FIG. 5 shows, in lateral sectional view, an HEMT device according to a further embodiment of the present disclosure;

FIGS. 6A-6E show, in lateral sectional views, successive manufacturing steps of the HEMT device of FIG. 1; and

FIG. 7 shows the plot of the drain current of the HEMT device of FIG. 1 in different conditions of drain voltage, compared with an HEMT device according to the known art.

DETAILED DESCRIPTION

FIG. 1 shows, in a triaxial system of axes X, Y, Z orthogonal to one another, an HEMT device 1A of a normally-off type, including a semiconductor substrate 2; a semiconductor buffer layer 3 which extends over the substrate 2 and is designed to enable a better depletion of the two-dimensional electron gas (2DEG) in the overlying conductive channel; a channel layer 4 which extends over the buffer layer 3; a semiconductor barrier layer 6 which extends over the channel layer 4; an insulation layer 7, of dielectric material such as silicon nitride (Si₃N₄) or silicon oxide (SiO₂), which extends over a front side 6a of the barrier layer 6; and a gate region 8, which extends in the semiconductor body 3 between a source electrode 10 and a drain electrode 12. In one or more embodiments, the substrate 2 is made, for example, of silicon, silicon carbide (SiC), or sapphire (Al₂O₃). In one or more embodiments, the buffer layer 3 is made of aluminum gallium nitride (AlGaN), indium gallium nitride (InGaN) or, in general, of AlGaN or InGaN alloys. In one or more embodiments, the channel layer 4 is made of gallium nitride (GaN) or intrinsic InGaN and has a thickness comprised between approximately 5 nm and 400 nm, e.g., approximately 15 nm. In one or more embodiments, the barrier layer 6 is made of intrinsic aluminum gallium nitride (AlGaN) or, more in general, of compounds based upon ternary or quaternary alloys of

gallium nitride, such as $\text{Al}_x\text{Ga}_{1-x}\text{N}$, AlInGa_xN , $\text{In}_x\text{Ga}_{1-x}\text{N}$, $\text{Al}_x\text{In}_{1-x}\text{Al}$, and has a thickness comprised between approximately 5 nm and 400 nm, e.g., approximately 15 nm.

The substrate **2**, the buffer layer **3**, the channel layer **4**, the barrier layer **6**, and the insulation layer **7** lie in respective planes parallel to the plane XY and are stacked on one another in the direction Z.

The channel layer **4** and the barrier layer **6** form a heterostructure **13**. The substrate **2**, the buffer layer **3**, and the heterostructure **13** are defined, as a whole, by the term "semiconductor body **15**".

The gate region **8** is separated and insulated laterally (i.e., along X) from the source region **10** and drain region **12** by respective portions of the insulation layer **7**. The gate region **8** is of a recessed type; i.e., it extends in depth through the insulation layer **7** and completely through the barrier layer **6**, as far as the channel layer **4**.

In other words, the gate region **8** is formed in a trench **9** etched through the insulation layer **7** and the barrier layer **6**.

A gate dielectric layer **8a** extends in the trench **9** facing the bottom and the side walls of the trench **9**. The gate dielectric **8a** may further extend, optionally, outside of the trench **9**, i.e., on the insulation layer **7**. A gate metallization **8b** completes filling of the trench **9** and extends over the gate dielectric layer **8a**. The gate dielectric layer **8a** and the gate metallization **8b** form the gate region **8** of the HEMT device **1A**.

The gate region **8** has a first side **8'** facing the drain region **12** and a second side **8''** facing the source region **10**. The first and second sides **8'**, **8''** of the gate region **8** extend, at least in part, parallel to one another and to the plane XY.

According to one aspect of the present disclosure, an auxiliary channel **20** extends over a front side **6a** of the barrier layer **6** between, and electrically coupled to, the source region **10** and the drain region **12**. In particular, the auxiliary channel **20** extends between the first side **8'** of the gate region **8** and the drain region **12**, and between the second side **8''** of the gate region **8** and the source region **10**. However, the portion of auxiliary channel that extends between the gate region **8** and the source region **10** may be absent.

In even greater detail, the auxiliary channel **20** extends between, and in contact with, a portion of the source region **10** and a respective portion of the gate oxide **8a** that defines the second side **8''** of the gate region **8**, and further in direct contact with the drain region **12**. However, the auxiliary channel **20** is not in direct contact with the first side **8'** of the gate region **8**, but at a distance therefrom. Thus, the auxiliary channel **20** extends in the proximity of the first side **8'** without ever being in direct contact therewith. The auxiliary channel **20** extends at a distance d_1 (measured in the direction X) from the first side **8'** of the gate region **8** chosen so that the electrical field is not excessively high on the first side **8'**. An electrical field is considered too high if it causes, or may cause, breakdown of the gate dielectric.

The present applicant has found that values of the distance d_1 equal to, or greater than, 0.5 μm are sufficient to satisfy the aforementioned conditions for the choice of d_1 .

According to one embodiment of the present disclosure, in the presence of a gate electrode or gate field plate **30**, the auxiliary channel **20** extends laterally offset with respect to the metal layer that provides the field plate **30** by a maximum distance (measured along X) not greater than a value d_2 . The value of distance d_2 is chosen so that there do not arise the problems, discussed with reference to the known art, of depletion of the two-dimensional electron gas (2DEG) and increase of the ON-state resistance as a result

of the trapping phenomena. The exact choice of d_2 may be made experimentally, by experimental tests on a test device.

The present applicant has found that values of the distance d_2 equal to, or smaller than, 0.5 μm are such as to overcome the drawbacks of the known art.

The auxiliary channel **20**, according to one embodiment, is made of gallium nitride (GaN) with an N-type doping, in particular with a density of dopant species comprised between $1 \cdot 10^{18} \text{ cm}^{-3}$ and $1 \cdot 10^{19} \text{ cm}^{-3}$, in particular $1 \cdot 10^{18} \text{ cm}^{-3}$. In this case, the thickness of the auxiliary channel **20** is comprised between 5 nm and 100 nm, in particular 50 nm.

In an HEMT **1B** according to an alternative embodiment, shown in detail in FIG. 2, the auxiliary channel **20** is a heterostructure including a layer of aluminum gallium nitride (AlGaN) **22** overlying a layer of gallium nitride (GaN) **24**. The AlGaN layer **22** has a thickness comprised between 5 nm and 50 nm, with aluminum concentration comprised between 15% and 50% (for example, 25%); the GaN layer **24** has a thickness comprised between 2 nm and 50 nm, for example 8 nm.

With reference to the barrier layer **6**, in both of the embodiments of FIGS. 1 and 2, it is preferably formed by two intermediate AlGaN layers **6'**, **6''** having concentrations of aluminum different from one another. According to an aspect of the present disclosure, the concentration of aluminum in the second intermediate layer **6''** is lower than the concentration of aluminum in the first intermediate layer **6'**. In particular, the first intermediate layer **6'**, which extends in direct contact with the channel layer, is made of AlGaN with a concentration of aluminum comprised between 10% and 40%, for example 25%, whereas the second intermediate layer **6''**, which extends directly over the first intermediate layer **6'**, is made of AlGaN with a concentration of aluminum lower than the previous one, namely, comprised between 5% and 30%, for example 15%, or else with a profile of concentration of aluminum decreasing in the direction Z moving away from the first intermediate layer **6'** (e.g., 30% of aluminum at the interface with the first intermediate layer **6'** and 5% of aluminum at the front side **6a**). The second intermediate layer **6''** further includes silicon doped with N-type dopant species.

This conformation of the barrier layer **6** enables reduction of the barrier between the auxiliary channel **20** and the barrier layer **6**.

During operation of the HEMT **1A**, **1B**, the charge carriers flow from the source region **10** to the drain region **12**, following the conductive paths designated by P_1 and P_2 in FIG. 1. As may be noted, in the portion of active area comprised between the gate region **8** and the source region **10**, the conductive paths P_1 and P_2 coincide; instead, in the portion of active area comprised between the gate region **8** and the drain region **12**, the conductive paths P_1 and P_2 do not coincide. Here, part of the charge carriers flows towards the drain region **12** passing through the two-dimensional electron gas (2DEG) in the channel **4** (path P_1), whereas part of the charge carriers flows towards the drain region **12** passing through the two-dimensional electron gas (2DEG) in the channel **4**, the barrier layer **6**, and the auxiliary channel **20**.

The choice, by the charge carriers, of the conductive path P_1 or P_2 is a function of the electrical resistance encountered in said path by the charge carriers.

In the case of undesired increase of the resistance R_{ory} in the channel layer **4** (as a result of the known trapping phenomena) the conductive path P_2 is privileged over the conductive path P_1 . In this way, during switching operating conditions of the HEMT **1A** where, as a result of the traps

in the channel layer **4**, the resistance *R* increases, there always exists an alternative path for the current, i.e., the one offered by the auxiliary channel **20**.

Operation of the HEMT device **1A** is thus not inhibited by the traps in the channel layer **4**.

The distance d_1 between the first side **8'** of the gate region **8** and the auxiliary channel **20** guarantees that, at the operating voltages considered (e.g., 400 and 600 V), the electrical field at the gate region **8** is not of an excessively high value such as to break the gate oxide **8a**.

According to a further aspect of the present disclosure, illustrated in FIG. **3**, an HEMT **1C** (according to any of the embodiments of FIG. **1** or FIG. **2**) further has a field-plate metal layer **30**, which extends as prolongation of the gate metallization **8b** towards the drain region **12** until it overlies (in top plan view or, equivalently, in the direction *Z*) the auxiliary channel **20**. The auxiliary channel **20** and the field-plate metal layer **30** are separated from one another by the insulation layer **7** and, if present, the gate dielectric **8a**.

Alternatively to the HEMTs **1A**, **1B**, **1C** with a field-plate metal layer **30** of a gate-connected type, there may be present one or more field plates of the source-connected type, i.e., electrically coupled to the metallization of the source region **10**, in HEMTs **1D**, **1E** as illustrated in FIGS. **4** and **5**, respectively (a source-connected field plate is identified by the reference number **34**).

With reference to the HEMT **1D** of FIG. **4**, the field-plate metal layer **34** extends between the gate region **8** and the drain region **12** in parallel to the auxiliary channel **20**, until it overlaps the latter (in top plan view or, equivalently, in the direction *Z*). The auxiliary channel **20** and the field-plate metal layer **34** are separated from one another by the insulation layer **7**, by a passivation layer **32** and, if present, by the gate dielectric **8a**. The passivation layer **32** has the function of insulating electrically the field-plate metal layer **34** from the gate region **8**.

According to the HEMT **1E** shown in FIG. **5**, the auxiliary channel **20** extends laterally offset (in the direction *X*) with respect to the field-plate metal layer **34**, i.e., not overlapping it (in the direction *Z*).

In this case, the maximum distance, measured in the direction *X*, between the edge that delimits the end of the field-plate metal layer **34** and the edge that defines the start of the auxiliary channel **20** is d_3 and has a value chosen so that there is not created a 2DEG region excessively depleted from the traps present in the buffer.

The value of d_3 is, in particular, equal to, or less than, 0.5 μm .

When both the gate field plate **30** and the source field plate **34** are present, the auxiliary channel **20** extends so that it is in at least one of the two conditions mentioned above with reference to FIGS. **3-4**, i.e., that (i) the auxiliary channel **20** at least partially overlaps one between the gate field plate **30** and the source field plate **34**; and/or (ii) the auxiliary channel **20** extends offset with respect to both the gate field plate and the source field plate **30**, **34** and at a distance, measured in the direction *X*, not greater than d_2 or d_3 from at least one between the gate field plate **30** and the source field plate **34**.

Described in what follows, with reference to FIGS. **6A-6E**, are steps for manufacturing the HEMT device **1A** of FIG. **1**, although most of the same steps may be employed for manufacturing the HEMTs **1B-1E** of FIGS. **2-5**, with small modifications discussed below.

FIG. **6A** shows, in cross-sectional view, a portion of a wafer **50** during a step for manufacturing the HEMT device, according to one embodiment of the present disclosure. Elements of the wafer **50** that are common to the ones

already described with reference to FIG. **1** and shown in FIG. **1**, are designated by the same reference numbers and are not described in detail any further.

In particular, the wafer **50** is provided, comprising: the substrate **2**, made, for example, of silicon (Si) or silicon carbide (SiC) or aluminum oxide (Al_2O_3), having a front side **2a** and a rear side **2b** opposite to one another in a direction *Z*; the buffer layer **3** on the front side **2a** of the substrate **2**, for example of aluminum gallium nitride (AlGaIn) or of indium gallium nitride (InGaIn); the channel layer **4**, for example of gallium nitride (GaN), having its own underside **4a** that extends adjacent to, and overlying, the buffer layer **3**; and the barrier layer **6**, which extends over the channel layer **4**. The barrier layer **6** and the channel layer **4** form the heterostructure **13**.

According to one or more embodiments of the present disclosure, formation of the barrier layer **6** envisages: formation of a first intermediate layer **6'** on the channel layer by depositing AlGaIn (e.g., via MOCVD or MBE) until a thickness is reached comprised between 5 nm and 20 nm, for example, 8 nm; and formation of a second intermediate layer **6''** by depositing AlGaIn and doped silicon with a doping level of $1 \cdot 10^{18} \text{ cm}^{-3}$ on the first intermediate layer **6'**, until a thickness comprised between 5 nm and 20 nm, for example 8 nm, is reached.

During deposition of the first intermediate layer **6'**, the concentration of aluminum is adjusted so that it is comprised between 10% and 40%; during deposition of the second intermediate layer **6''**, the concentration of aluminum is adjusted so that it is comprised between 50% and 30%.

Alternatively, the second intermediate layer **6''** is formed so that it has a profile of concentration of aluminum decreasing in the direction *Z* moving away from the first intermediate layer **6'** (e.g., 30% of aluminum at the interface with the first intermediate layer **6'** and 5% of aluminum at the front side **6a**).

Next, on the front side **6a** of the barrier layer **6** an auxiliary channel layer **56** is formed, for example by depositing gallium nitride, GaN, with N-type doping (e.g., by MOCVD or MBE), according to the embodiment already described with reference to FIG. **1**.

Alternatively, according to the embodiment of FIG. **2**, the auxiliary channel layer **56** is formed by depositing a first layer of gallium nitride (GaN), of an intrinsic type and, then, over it, an AlGaIn layer. Deposition of both the GaN layer and the AlGaIn layer that form the auxiliary channel layer **56** is carried out by deposition (e.g., via MOCVD or MBE), modulating selectively the desired amount of aluminum in both layers.

Then (FIG. **6B**), a step of masked etching of the auxiliary channel layer **56** is carried out to remove first selective portions thereof at a region **57'** where, in subsequent machining steps, the gate trench **9** will be formed, and to remove further second selective portions of the auxiliary channel layer **56** that extend alongside the region **57'** for a length, in the direction *X*, equal to d_1 (region **57''** identified in FIG. **6B**). In particular, the removed second selective portions of the auxiliary channel layer **56** extend as lateral prolongation of the first selective regions, towards the portion of wafer **50** that will house the drain region of the HEMT device **1A-1E**. This process step defines the distance d_1 between the drain region **8** and the auxiliary channel **20**, as described previously.

Then, once again with reference to FIG. **6B**, formed on the wafer **50** (and thus on the auxiliary channel layer **56** thus structured and at the regions **57'**, **57''**) is a passivation layer **52**, of dielectric or insulating material, for example silicon

nitride (SiN) or silicon oxide (SiO₂). The passivation layer 52 has a thickness comprised between 5 nm and 300 nm, for example 100 nm, and is formed by CVD or atomic-layer deposition (ALD), and, at the end of the manufacturing steps, will form the insulation layer 7.

Next (FIG. 6C), the passivation layer 52 is selectively removed, for example by lithographic and etching steps, for removing selective portions thereof in the region 57' of the wafer 50 where the gate region 8 of the HEMT device 1 is to be formed.

The etching step may stop at the underlying barrier layer 6 (to provide an HEMT of a normally-on type), or else it may proceed partially into the barrier layer 6 (the latter embodiment is shown in FIG. 6B). In this second case, a surface portion 4' of the underlying channel layer 4 is exposed. Etching of the barrier layer 6 is carried out, for example, by dry etching.

The trench 9 is thus formed, which extends throughout the thickness of the passivation layer 52 and for an underlying portion of the barrier layer 6.

There is then formed, for example by deposition, the gate-dielectric layer 8a, made, for example, of a material chosen from among aluminum nitride (AlN), silicon nitride (SiN), aluminum oxide (Al₂O₃), and silicon oxide (SiO₂). The gate-dielectric layer 8a has a thickness chosen between 1 and 50 nm, for example 20 nm.

Next (FIG. 6D), a step of deposition of conductive material on the wafer 30 is carried out to form a conductive layer 58 on the gate dielectric layer 8a, in particular in order to fill the trench 9. For example, the conductive layer 58 is made of metal material, such as tantalum (Ta), tantalum nitride (Ta₂N), titanium nitride (TiN), palladium (Pa), tungsten (W), tungsten silicide (WSi₂), titanium/aluminum (Ti/Al), or nickel/gold (Ni/Au).

The conductive layer 58 is then selectively removed by lithographic and etching steps in themselves known for eliminating it from the wafer 50 except for the portion thereof that extends in the trench 9, thus forming the gate metallization 8b. During the same step, using an appropriate mask for etching of the conductive layer 58, it is further possible to define, in a per se known manner, the gate field plate 30, described with reference to FIG. 3.

The gate metallization 8b and the gate dielectric 8a form, as a whole, the recessed-gate region 8 of the HEMT device of FIG. 1.

Then (FIG. 6E), one or more further steps of masked etching of the gate dielectric 8a, of the passivation layer 52, of the auxiliary channel layer 56, and of the barrier layer 6 are carried out to remove selective portions thereof that extend in regions of the wafer 50 where the source and gate regions 10, 12 of the HEMT device 1A are to be formed.

Removal of the selective portions of the passivation layer 52 leads to formation of the insulation layer 7 illustrated in FIG. 1. Likewise, removal of selective portions of the auxiliary channel layer 56 leads to formation of the auxiliary channel 20 illustrated in FIG. 1.

In particular, openings are formed on opposite sides (sides 8' and 8'') of the gate region 8, and at a distance from the gate region 8, until the channel layer 4 is reached.

Next, a step of formation of ohmic contacts is carried out to provide the source and drain regions 10, 12, by depositing conductive material, in particular metal such as titanium (Ti) or aluminum (Al), or alloys or compounds thereof, by sputtering or evaporation, on the wafer 50. A next step of etching of the metal layer thus deposited is then carried out to remove said metal layer from the wafer 50 except for the

metal portions that extend within source and drain openings to form therein the source region 10 and the drain region 12, respectively.

Next, a step of rapid thermal annealing (RTA), for example at a temperature comprised between approximately 500 and 900° C. for a time of from 20 s to 5 min, enables formation of electrode ohmic contacts of the source electrode 10 and drain electrode 12 with the underlying channel layer (having the two-dimensional gas 2DEG).

The HEMT device 1A shown in FIG. 1 is thus formed.

FIG. 7 represents the plot (obtained by simulation) of the drain current (I_D) (which is indicative of the ON-state resistance R_{on}) as a function of the drain stresses, for two biasing values provided by way of example (400 V and 600 V), and in both the case where the auxiliary channel is present according to the present disclosure and in the case where the auxiliary channel is absent according to the prior art. In particular, with reference to FIG. 7:

the curve C₁ shows the plot of the drain voltage VD as a function of the drain current in pre-stress conditions in an HEMT device provided with the auxiliary channel 20, according to the present disclosure;

the curve C₂ shows the plot of the drain voltage as a function of the drain current in pre-stress conditions in an HEMT device according to the known art, without of the auxiliary channel 20;

the curve C₃ represents the plot of the drain voltage as a function of the drain current in post-stress conditions (400 V) in an HEMT device provided with the auxiliary channel 20, according to the present disclosure;

the curve C₄ represents the plot of the drain voltage as a function of the drain current in post-stress conditions (400 V) in an HEMT device according to the known art, without the auxiliary channel 20;

the curve C₅ represents the plot of the drain voltage as a function of the drain current in post-stress conditions (600 V) in an HEMT device provided with the auxiliary channel 20, according to the present disclosure; and

the curve C₆ represents the plot of the drain voltage as a function of the drain current in post-stress conditions (600 V) in an HEMT device according to the known art, without the auxiliary channel 20.

As may be noted, the presence of the auxiliary channel 20 (curves C₁, C₃, C₅) determines a marked increase in the drain current as compared to an embodiment that does not envisage it (curves C₂, C₄, C₆), in operating conditions comparable to one another.

Consequently, according to the present disclosure, the operating and functional characteristics of the HEMT device 1 are improved as compared to what is available according to the prior art.

An HEMT device provided according to the present disclosure shows high values of current irrespective of the operating conditions, and irrespective of the traps present in the channel layer (which does not require any specific optimization for reduction of the traps). The performance of the device is markedly improved.

Finally, it is clear that modifications and variations may be made to what is described and illustrated herein, without thereby departing from the scope of the present disclosure.

For example, according to further embodiments (not shown), the semiconductor body 5 may comprise just one or else more than one layers of GaN, or GaN alloys, appropriately doped or of an intrinsic type.

Further, according to one embodiment, the source region 10 and the drain region 12 extend in depth in the semicon-

ductor body **5**, completely through the barrier layer **6** and partially through the channel layer **4**, and terminate within the channel layer **4**.

Alternatively, the metallizations of the source and drain contacts may further be provided only partially recessed within the barrier layer **6**, or else facing the front side **6a** of the barrier layer **6**.

The metallizations of the source, drain, and gate contacts may be made using any material designed for the purpose, such as, for example, formation of contacts of AlSiCu/Ti, Al/Ti, or W-plug, etc.

Further, according to one embodiment, the gate region **8** does not extend completely through the barrier layer **6**, but terminates at the front side **6a** of the barrier layer; in this case, the HEMT device is of a normally-on type.

The various embodiments described above can be combined to provide further embodiments. These and other changes can be made to the embodiments in light of the above-detailed description. In general, in the following claims, the terms used should not be construed to limit the claims to the specific embodiments disclosed in the specification and the claims, but should be construed to include all possible embodiments along with the full scope of equivalents to which such claims are entitled. Accordingly, the claims are not limited by the disclosure.

The invention claimed is:

1. A device, comprising:

a semiconductor body including a first layer of a first III-V compound semiconductor material, a second layer of a second III-V compound semiconductor material over the first layer, and a third layer of a third III-V compound semiconductor material over the second layer;

a gate structure, which contacts the first layer in a first direction, contacts the second layer in a second direction that is different from the first direction, and is separated from a first portion of the third layer in the second direction, a distance between a gate electrode of the gate structure and the first portion of the third layer being substantially equal to or larger than 5 μm ; and

a source structure that contacts the first layer in the first direction, contacts the second layer in the second direction, and contacts a second portion of the third layer in the second direction, wherein the second portion of the third layer contacts the gate structure in the second direction.

2. The device of claim **1**, wherein the first III-V compound semiconductor material is GaN.

3. The device of claim **1**, wherein the second III-V compound semiconductor material is one or more of a ternary of GaN or a quaternary alloys of GaN.

4. The device of claim **1**, wherein the third III-V compound semiconductor material is GaN with an N-type doping.

5. The device of claim **1**, wherein the second layer includes a first sub-layer and a second sub-layer positioned directly over the first sub-layer, a material of the first sub-layer and a material of the second sub-layer including same material elements with different element concentrations.

6. The device of claim **5**, wherein the first sub-layer is AlGaN of a first Al concentration, and the second sub-layer is AlGaN of a second Al concentration, the second Al concentration being smaller than the first Al concentration.

7. The device of claim **1**, wherein the first III-V compound semiconductor material and the second III-V compound semiconductor material have different band gaps.

8. The device of claim **1**, wherein the gate structure includes a field plate that overlaps both the first layer and the second layer in the first direction, and is laterally offset from the first portion of the third layer in the second direction.

9. The device of claim **8**, wherein the distance between the gate electrode and the first portion of the third layer in the second direction is larger than a dimension of the field plate extending from the gate electrode in the second direction.

10. The device of claim **1**, further comprising a drain structure that contacts the first layer in the first direction, contacts the second layer in the second direction, and contacts the first portion of the third layer in the second direction.

11. A transistor, comprising:

a channel layer, which forms a main conductive channel, a barrier layer over the channel layer;

an insulation layer over the barrier layer;

a gate including a gate electrode and a gate dielectric layer;

a drain electrode positioned by a first side of the gate, and contacting the channel layer;

a source electrode positioned by a second side of the gate, and contacting the channel layer;

an auxiliary channel layer extending over the barrier layer, in electrical contact with the drain electrode, and spaced apart from the gate electrode by the insulation layer; and

a gate field plate integral to the gate electrode and extending from the first side of the gate electrode over the insulation layer, and directly overlapping the gate dielectric layer.

12. The transistor of claim **11**, wherein the auxiliary channel layer is spaced apart from first side of the gate electrode by a distance that is equal to, or greater than, 0.5 μm along said direction.

13. The transistor of claim **11**, wherein the auxiliary channel layer is of gallium nitride with N-type doping.

14. The transistor of claim **11**, wherein the auxiliary channel layer includes:

a first layer of GaN; and

a second layer of AlGaN positioned over the first layer, the second layer having an aluminum concentration ranging between 15% and 50%.

15. The transistor of claim **11**, wherein:

the channel layer includes a first material;

the barrier layer includes a second material that has a different band gap from that of the first material.

16. The transistor of claim **11**, wherein the barrier layer include:

a first intermediate layer of aluminum gallium nitride having an aluminum concentration ranging between 10% and 40%; and

a second intermediate layer, which extends over the first intermediate layer and includes aluminum gallium nitride having an aluminum concentration ranging between 5% and 30%.

17. A high-electron-mobility transistor (HEMT) device, comprising:

a main channel layer, which forms a main conductive channel;

a semiconductor barrier layer over the main channel layer;

an insulation layer over the semiconductor barrier layer;

a gate structure extending into the insulation layer, the gate structure including a gate electrode and a gate dielectric layer;

a drain electrode extending into the insulation layer and facing a first side of the gate structure;

11

a source electrode extending into the insulation layer and facing a second side of the gate structure that is opposite to the first side; and

an auxiliary channel layer extending within the insulation layer and over the semiconductor barrier layer, the auxiliary channel layer being in electrical contact with the drain electrode, being separated from the gate structure by the insulation layer, and being coplanar with the insulation layer with respect to a top surface of the semiconductor barrier layer.

18. The HEMT device of claim 17, further comprising a gate field plate which contacts the gate electrode and extends over the insulation layer, the gate field plate being laterally offset from the auxiliary channel layer.

19. A high-electron-mobility transistor (HEMT) device, comprising:

a semiconductor body including a heterojunction structure that forms a main conductive channel of the HEMT device;

a dielectric layer on the semiconductor body;

a gate structure, a drain electrode, and a source electrode at least partially in the semiconductor body, the gate

12

structure including a gate electrode and a gate dielectric layer, the gate dielectric layer extending over the dielectric layer, the drain electrode facing a first side of the gate electrode, and the source electrode facing a second side, opposite to the first side, of the gate electrode;

an auxiliary channel layer, which extends over the heterojunction structure between the gate electrode and the drain electrode, is in electrical contact with the drain electrode, is spaced apart from the first side of the gate electrode, and forms a conductive path additional to the main conductive channel for charge carriers to flow between the source electrode and the drain electrode; and

a field plate integral to the gate electrode and extending from the first side of the gate electrode over the dielectric layer, and directly overlapping the gate dielectric layer.

20. The HEMT device of claim 19, further comprising a source field plate electrically coupled to the source electrode and overlapping the dielectric layer.

* * * * *